



FORMCAST

Precasting Release Agents

FORMPOL EXTRA DWF30 Dewatering and Rust Preventative System

Description

A specially formulated product based on a blend of preservative oils and additives, providing excellent surface de-watering characteristics whilst simultaneously providing an economical temporary protective coating to ferrous and non-ferrous metal moulds or forms. The product allows effective storage and shipment of steel and metal members and equipment.

Advantages

- An effective combined de-watering and rust prevention system.
- Very economical and easy to use.
- Non-staining material.
- Non-reactive with pre-painted surfaces.
- Easily removed prior to subsequent treatments.
- Fast drying time, approx 1 hour.

Properties

| | |
|-------------------|---|
| Appearance: | Clear Red/Brown liquid. |
| Specific Gravity: | 0.817 @ 20°C. |
| Flash Point: | 36°C (Pensky Martin Closed Cup). |
| Viscosity: | 3.3 cSt @ 20°C |
| Drying Time: | Approx 1 hour. |
| Storage Life: | Indefinite in manufacturer's sealed containers. |

Application

Ensure surfaces are clean, free of dust, grease, oils or other deleterious materials prior to treatment. If members are hosed or jet washed, excessive water should be removed prior to application of **DWF 30**. Surface moisture will be displaced by the de-watering action of the product. Members may be sprayed, brushed or dipped to provide adequate treatment for 40 days protection.

Coverage

30-60 m²/litre dependent on surface finish and ambient temperature.
50m²/litre @ 4.5 micron film thickness.

Limitations

FORMPOL DWF 30 should be removed prior to casting as contact may give rise to staining and excessive dusting.

Storage & Handling

DWF30 is supplied ready to use in manufacturer's sealed containers and should not be diluted. **DWF30** is flammable and should not be used in enclosed areas with poor ventilation due to vapour risk. As product is flammable, drums should be stored at ambient temperatures away from sources of ignition.

Packaging

FORMPOL EXTRA DWF30 is supplied in 205 litre and 25 litre sealed containers.

formworkdirect.co.uk
TEL:
(+44) (0)151 532 0179
EMAIL
sales@formworkdirect.co.uk



formworkdirectmalta.com
TEL:
(+356) 9947 3031
EMAIL
sales@formworkdirectmalta.com